

TUBULAR STEEL POLES FOR OVERHEAD LINES**1 SCOPE:**

This specification covers the general requirements towards design, manufacture, testing at manufacturers works, supply and delivery for tubular steel poles of circular cross section (swaged type) for overhead lines.

2 STANDARD:

2.1 The tubular steel poles shall conform to the latest edition of Indian Standard specification IS: 2713 (Part – I, III): 1980 or any other authoritative standards (as amended up-to- date) except where specified otherwise in this specification.

3 Topography and Climatic Condition:

3.1 The materials offered, shall be suitable for operation in tropical climate and will be subjected to the sun and inclement weather and shall be able to withstand wide range of temperature variation. For the purpose of design, average atmospheric temperature may be considered to be 50°C with humidity nearing saturation.

4 Materials:

4.1 The materials used in construction of tubular steel poles shall be of the tested quality of steels of minimum tensile strength 540 MPa (: 55 Kgf/mm²).

4.2 The materials, when analysed in accordance with IS: 228 (Part-III: 1972) and IS : 228 (Part-IX) shall not show sulphur and phosphorous contents of more than 0.060 percent each.

5 Types, Size and construction:

5.1 Tubular Steel Poles shall be swaged type.

5.2 Swaged poles shall be made of seamless or welded tubes of suitable lengths swaged and jointed together. No circumferential joints shall be permitted in the individual tube lengths of the poles. If welded tubes are used they shall have one longitudinal weld seam only: and the longitudinal welds shall be staggered at each swaged joint.

5.3 Swaging may be done by any mechanical process. The upper edge of each joint shall be chamfered if at an angle of about 45°. The upper edge need not be chamfered if a circumferential weld is to be deposited in accordance with clause No. 5.3 2 of IS: 2713 (Part-I):1980.

5.4 The length of joints on swaged poles shall be in accordance with clause No. 5.4 of IS: 2713 (Par-I): 1980.

5.5. Poles shall be well-finished, clean and free from harmful surface defects. Ends of the poles shall be cut square. Poles shall be straight, smooth and cylindrical. The weld joints, if any, shall be of good quality, free from scale, surface defects, cracks, etc.

5.6. Tolerances for outside diameter, thickness, length, weight and straightness shall be in accordance with IS: 2713 (Part-I) : 1980.

5.7. The poles shall be coated with black bituminous paint conforming to IS: 158-1968 throughout, internally and externally, upto the level which goes inside the earth. The remaining portion of the exterior shall be painted with one coat of red oxide primer as specified in IS: 2074-1979.

6 Earthing Arrangements:

6.1 For earthing arrangement a through hole of 14mm diameter shall be provided in each pole at a height of 300mm above the planting depth.

7 Tests and Test Certificates:

7.1 The following tests shall be conducted on finished poles :

- A. Tensile test and chemical analysis for sulphur and phosphorous,
- B. Deflection test,
- C. Permanent set test, and
- D. Drop test.

7.2 In addition to above verification of dimensions as per IS: 2713 (Part-III) : 1980 shall be carried out during acceptance lots.

7.3 Number of poles selected for conducting different tests shall be in accordance to clause No. 10.1.1 and No. 10.1.12: of IS: 2713 (Part-I) 1980.

7.4 Tests shall be carried out before supply of each consignment at the manufacturers works and test certificates should be submitted to the purchaser for approval prior to delivery.

7.5 Re-tests, if any, shall be made in accordance with IS: 2713 (Part-I) 1980.

7.6 Purchaser reserves the right to inspect during manufacturing and depute his representative to inspect/test at the works.

7.7 If any extra cost is required for carrying out the above specified tests, the same shall be borne by the supplier.

8 Marking:

8.1 The poles shall be marked with designation, manufacturer's identification, year of manufacture and name of the purchaser: Employer Name; RGGVY XII Plan

8.2 The poles may also be marked with the ISI certification mark.

9 Guaranteed technical particulars:

9.1 The tenderer shall furnish all necessary guaranteed technical particulars in the prescribed Performa enclosed hereinafter.

10 Performance:-

10.1 The supplier shall furnish a list of the major supplies effected during the last 3 (three) years indicating the volume of supply and actual delivery dates along with the bids.

10.2 Supplier may not be considered if the past manufacturing experience is found to be less than 3 (three) years.

11 Deviation:-

11.1 Any deviation in technical specification shall be clearly indicated with sufficient reasons thereof. Purchaser shall however reserve the right to accept and/or reject the same without assigning any reasons whatsoever.

ANNEXURE –‘A’

SPECIFIC TECHNICAL REQUIREMENTS FOR
TUBULAR STEEL POLES : SWAGED TYPE

	9 meters long	11 meters long	13 meters long
1) Standard	IS: 2713 (Pat-I and III): 1980 as amended upto date		
2) Type of Pole	Swaged Type		
3) Designation	540 SP 28	540 SP 52	540 SP 72
4) Overall Length	9 meters	11 meters	13 meters
5) Planting depth	1.5 meters	1.8 meters	2.0 meters
6) Height above ground	7.5 meters	9.2 meters	11.0 meters
7) Effective length of Each section.			
a) Bottom	5.0 meters	5.6 meters	5.80 meters
b) Middle	2.0 meters	2.7 meters	3.60 meters
c) Top	2.0 meters	2.7 meters	3.60 meters
8) Outside diameter and Thickness of each Section.			
a) Bottom	139.7x 4.50 mm	165.1x4.50 mm	219.1x5.90 mm
b) Middle	114.3x3.65 mm	139.7x4.50 mm	193.7x4.85 mm
c) Top	88.9x3.25 mm	114.3x3.65 mm	165.1x4.50 mm
9) Joint Length (in cm.):			
a) Bottom (J2)	30 cm.	35 cm.	45 cm.
b) Top (J1)	23 cm.	30 cm.	40 cm.
10) Approximate weight of Pole	113 Kg.	175 Kg.	343 Kg.
11)Point of application of load below/top (mtr.)	0.3 mtr.	0.6 mtr.	0.6 mtr
12) Breaking load (inKgf)	478	567	1084
13) Working load with factor of Safety : 2.5 (in Kgf)	191	227	435 Kg.
14) Crippling load (inKgf)	339	403	770 Kg.
15) Load for permanent set Not exceeding 13mm (in Kgf)	232	276	527 Kg.
16) Load for Temporary Deflection of 157.5 mm (in Kgf)	76	74	121
17) Tolerance	As per IS : 2713 (Part-I & Part-III): 1980		
18) Finish		-do-	
19) Manufacturing clause		-do-	